

Sof'n-Soil[®] Lawn and Garden Gypsum

	Location	Chemical Analysis				Screen Analysis	
		Calcium Sulfate Dihydrate (CaSO ₄ ·2H ₂ O)		Calcium (Ca)	Sulfur (S)	Plus 100 Mesh	Minus 100 Mesh
		Typical	Minimum Guarantee				
Fine Grind	Empire, NV	84%	82%	19.6%	15.7%	11%	89%
Coarse Grind	Baltimore, MD	85%	83%	19.7%	15.8%	76%	24%
	Detroit, MI	89	88	20.7	16.6	76	24
	Shoals, IN	88	85	20.5	16.4	78	22

